

3M™ Optically Clear Adhesive 8146-x

Product Description

3M™ Optically Clear Adhesive 8146-x is a new pressure sensitive adhesive technology that provides crystal clear, high reliability optical coupling and mechanical joining for various transparent materials.

3M Adhesive 8146-x is used for capacitive touch sensor film and lens bonding application. It is bare ITO compatible and outgassing resistant for PMMA substrates.

Key Attributes

- High adhesion
- Easy to convert and cut
- ITO compatible
- Out-gassing resistant
- Whitening resistant
- Great option for bonding, PMMA, glass, PET, and other high surface energy & some lower surface energy substrates

Product Construction

Product	3M™ Optically Clear Adhesive				
	8146-1	8146-2	8146-3	8146-4	8146-5
Adhesive Type:	Acrylic	Acrylic	Acrylic	Acrylic	Acrylic
Adhesive Carrier:	None	None	None	None	None
Approximate Thickness:					
Release Liner	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester
Adhesive	1.0 mil (25 micron)	2.0 mil (50 micron)	3.0 mil (75 micron)	4.0 mil (100 micron)	5.0 mil (125 micron)
Release Liner	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester	3.0 mil (75 micron) Polyester



Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Refractive Index

Abe Refractometer (± 0.0005 measured for Sodium D line @ 25°C)

3M™ Optically Clear Adhesive 8146-x	
	1.474

Haze

Haze measured according to ASTM D1003-92.

3M™ Optically Clear Adhesive 8146-x	
	<1.0%

Color

ASTM-E1164-07 / CIELAB

(BYK Gardner TCS Plus spectrophotometer, model 8870)

3M™ Optically Clear Adhesive 8146-x	
	L* = 97.0
	a* = -0.07
	b* = 0.10

Peel Adhesion:

ASTM D3330 modified,

180 degree peel, 12 in./min. (305 mm/min.) To glass and lens bonding adhesives.

Condition	Unit	3M™ Optically Clear Adhesive									
		8146-1		8146-2		8146-3		8146-4		8146-5	
		oz/in	(N/100mm)	oz/in	(N/100mm)	oz/in	(N/100mm)	oz/in	(N/100mm)	oz/in	(N/100mm)
20 min dwell at RT	PMMA	30	33	40	43	44	48	50	54	51	55
20 min dwell at RT	PC	31	34	42	45	47	51	53	57	55	59
20 min dwell at RT	Glass	41	44	50	54	54	58	60	65	61	66

Shear Adhesion

ASTM D-3657

1/2" x 1" Overlap, minutes to failure.

3M™ Optically Clear Adhesive 8146-x	
Heat Aged 1000 gram, stainless steel	>10,000

Shelf Life

A Product retains its performance and properties for two years from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% relative humidity.

Storage in a plastic bag is recommended.

Application Techniques

For maximum bond strength the surface should be thoroughly cleaned and dried. To obtain greatest benefit, laminations should be done in the cleanest environment possible with static charge elimination.

Bond strength can be improved with firm application pressure and moderate heat causing the adhesive to develop intimate contact with the bonding surface.

General Information

- Light transmission >99% when corrected for reflection losses.
- Free of birefringence with no film carrier.
- High temperature, humidity, and UV resistance.
- Long term durability without yellowing, delaminating or degradation.
- High cohesive and peel strength for reliably bonding most transparent substrates.
- 3M™ Optically Clear Adhesive 8146-x is coated and converted in a clean room.
- 3M™ Optically Clear Adhesives are inspected to reduce the occurrence of bubbles, dirt, gels and other optical distortions.
- Wound on plastic cores and wrapped in plastic to eliminate paper fiber contamination.
- Wound on plastic cores and wrapped in plastic to eliminate paper fiber contamination.
- Two film liners for optimum adhesive smoothness and differential release for ease of processing and protection from contamination.

Application Ideas

- Touchscreens for bonding film and glass laminate.
- Transparent graphic overlays.
- Projection screens.
- Avionics/military displays.
- Optical management films for LCD.

Processing

Laminating

Recommended nip roll or roller platen press type laminator to maintain optical aesthetics when laminated.

Hand Lamination not advised. Use best process control standards Possible to control variables.

(See **3M Laminating Technical Bulletin** for additional information)

Die Cutting

Use high precision, tight tolerance tooling designed to cleanly cut film and pressure-sensitive adhesive.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Electronics Markets Materials Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
1-800-251-8634 phone
651-778-4244 fax
www.3M.com/electronics

3M is a trademark of 3M Company.
Please recycle. Printed in U.S.A.
© 3M 2013. All rights reserved.
60-5002-0674-7

